# Novel constant-cladding tapered-core ytterbium-doped fiber for high power fiber laser oscillator

Yun Ye<sup>1†</sup>, Xianfeng Lin<sup>2†</sup>, Xiaoming Xi<sup>1</sup>, Chen Shi<sup>1</sup>, Baolai Yang<sup>1</sup>,

Hanwei Zhang<sup>1</sup>, Xiaolin Wang<sup>1\*</sup>, Jinyan Li<sup>2\*\*</sup> and Xiaojun Xu<sup>1</sup>

<sup>1</sup>College of Advanced Interdisciplinary Studies, National University of Defense Technology, Changsha 410073, China <sup>2</sup>Wuhan National Laboratory for Optoelectronics (WNLO), Huazhong University of Science and

Technology, Wuhan 430074, China

Abstract Power scaling based on traditional ytterbium-doped fibers (YDFs) is limited by optical nonlinear effects and transverse mode instability (TMI) in high-power fiber lasers. Here, we propose a novel long-tapered fiber with a constant cladding and tapered core (CCTC) along its axis direction. The tapered core region of the fiber is designed to enhance the stimulated Raman scattering (SRS) threshold and suppress higher-order mode resonance in the laser cavity. The CCTC Yb-doped fiber was fabricated successfully with a modified chemical vapor deposition (MCVD) method combined with solution doping technology, which has a cladding diameter of 400  $\mu$ m and a varying core with a diameter of ~24  $\mu$ m at both ends and ~31  $\mu$ m in the middle. To test the performance of the CCTC fiber during high-power operation, an all-fiber laser oscillator based on a CCTC YDF was investigated experimentally. As a result, a maximum output power of 3.42 kW was achieved with an optical-to-optical efficiency of 55.2%, although the TMI effect was observed at an output power of ~3.12 kW. The measured beam quality (M<sup>2</sup> factor) was ~1.7, and no sign of Raman component was observed in the spectrum. We believe that

CCTC YDF has great potential to simultaneously mitigate the SRS and TMI effects, and further power scaling is promising by optimizing the structure of the YDF.

Key words: ytterbium-doped fiber; fiber design; high power; stimulated Raman scattering; transverse mode instability

Correspondence to: X. Wang and J. Li, Email: chinawxllin@163.com (X. Wang); ljy@mail.hust.edu.cn (J. Li). †These authors contributed equally to this work.

# I. INTRODUCTION

High-power fiber lasers have been broadly applied in various fields such as industrial processing, national security, medical sciences, and so on, owing to their advantages of high conversion efficiency, good beam quality, easy thermal management, and compact structure [1]. With the development of double-cladding fiber and high-brightness laser diodes (LDs), the output power of nearly single-mode fiber lasers has witnessed a remarkable growth in the past two decades [2-6]. However, as the output power increases, the occurrence of nonlinear effects, such as stimulated Raman scattering (SRS) [7] and transverse mode instability (TMI) [8], becomes the main limitation for further power scaling of continuous-wave (CW) broadband fiber lasers. To overcome the nonlinear effects, one of the most straightforward and effective strategies is to reduce the laser intensity in the core by applying large-mode-area (LMA) fibers. Unfortunately, a conventional LMA fiber normally implies a large core size, where not only fundamental mode but also higher-order modes are inevitably supported. When the output power exceeds a certain threshold, the thermally induced index grating caused by the mode coupling

will lead to the onset of the TMI effect, resulting in a deterioration of the beam quality and limitation of the power scaling [9].

In principle, it is possible to suppress the SRS or TMI effect by optimizing the configuration and parameters of the laser system, such as shifting the pump or signal wavelength [10] and optimizing the fiber coiling diameter [11] and the pump power distribution [12]. However, it is difficult to suppress both of them simultaneously, according to previous studies [13-15]. Numerous studies have focused on a fiber design to realize a single-mode operation in LMA fibers. Specially designed fibers, such as leakage-channel fiber [16], chirally-coupled-core fiber [17], multi-trench fiber [18], large-pitch fiber [19], and all-solid photonic bandgap fiber [20], have been proposed and manufactured to suppress a high-order mode (HOM) generation. However, none of the aforementioned fibers can be realized without precision refractive index control and complex fabrication processes. In addition, these fibers have seldom been employed in multi-kilowatt all-fiber laser systems because of the mismatching with conventional passive fiber, which is likely to result in some difficult problems such as fusion loss and mode distortion.

Unlike fibers with a complex transversal structure, a long tapered fiber with a gradually varying core size in the longitudinal dimension has a relatively simple structure [21]. Compared with conventional uniform double-cladding fiber, a long-tapered fiber has many advantages such as increasing the pump absorption, suppressing the nonlinear effects, and maintaining a good beam quality [22]. In addition, the conventional step-index profile makes the tapered fiber less sensitive to the fabrication process and packaging constraints, and it is therefore convenient to match the conventional double-clad passive fiber and apply it in the field of high-power fiber laser systems. There have been a number of applications using tapered fibers reported for both the pulsed and CW regimes. In 2017, researchers at the Russian Academy of Sciences presented

a sub-MW peak-power chirped pulse amplification based on an LMA polarization-maintaining tapered Yb-doped fiber [23]. In 2018, Fedotov et al. reported a linearly polarized CW and pulsed picosecond MOPA based on a birefringent tapered Yb-doped fiber with a record core diameter of 96 µm [24]. In 2018, researchers at Jena established a nanosecond fiber master oscillator power amplifier system, where a section of tapered fiber was adopted as the final amplification stage to achieve a peak power of 375 kW with a measured beam quality (M<sup>2</sup> factor) of 1.3–1.7 [25]. However, most of the reported tapered fiber lasers have been constructed based on a spatial optics configuration, which lacks stability and compactness [23-28]. In 2019, our research group conducted an experimental investigation into all-fiberized laser oscillators and amplifiers based on long tapered fibers [29, 30]. However, because of the larger core size at the output end, the M<sup>2</sup> factor of the output laser was greater than 2.0, indicating a high number of HOMs in the output. Moreover, the further power scaling of these two fiber lasers was still restricted by the TMI with an increase in the output power. Therefore, simultaneously mitigating the SRS and TMI effects, obtaining a good beam quality, and realizing a further power scaling of CW Ybdoped fiber lasers are urgent issues.

In this study, we proposed and demonstrated a novel constant-cladding tapered-core (CCTC) YDF for the first time, which is fabricated using an MCVD in conjunction with a solution doping technique. The CCTC fiber consists of a constant cladding diameter (diameter of ~400  $\mu$ m) and a varying core diameter (diameter of ~24  $\mu$ m at both ends and ~31  $\mu$ m in the middle). Based on this fiber, the laser performances, particularly the TMI and SRS characteristics, are investigated in detail by establishing a high-power all-fiber laser oscillator system. In the experiment, the maximum output power was scaled up to 3.4 kW with an optical

efficiency of ~55.2%, and the measured  $M^2$  factor degrades from 1.60 to 1.88, with no sign of the SRS effect within the spectrum.

## II. Fiber design and fabrication

In this part, we designed new tapered fibers with different tapered structures, including CCTC fibers, and conducted a numerical simulation based on the coupled-mode theory compared with the conventional uniform fiber [30]. In our simulation, four types of fibers with different core diameter distributions are considered and plotted, as shown in Fig. 1(a). We assume that the tapered fibers (Fibers II - IV) have a constant cladding diameter of 400 µm and a graded core diameter with a small core diameter of 25 µm at both ends and a large core diameter of 30 µm in the middle. Fibers II - IV correspond to the linear, convex, and concave CCTC fibers, respectively, which have symmetrical distributions along the fiber length. For comparison with the other tapered fibers, Fiber I is a conventional uniform fiber with a core diameter of 27.5 µm.

Taking the structure of the CCTC fiber into account, a numerical model of the copumped fiber amplifier is established based on rate equations and coupled mode theory. The central wavelength was 1080 nm. The pump and the signal power were set to 2 kW and 10 W, respectively. According to the fiber parameters we have assumed above, we defined the injected signal power as that fundamental mode (FM) power is nine-fold higher of HOMs power, where the input signal power of  $LP_{01}$ ,  $LP_{11}$ ,  $LP_{21}$  and  $LP_{02}$  modes was respective 9 W, 0.4 W, 0.4 W and 0.2 W. The power evolution and mode coupling were simulated in the fiber amplifier. The power distributions of the FM and HOMs are calculated, as shown in Fig. 1(b). From the simulation results, the HOMs power of these CCTC fibers first increases along the fiber length, and then decreases when the core diameter gradually decreases from the large core region to the small core region. This is due to that the variation of core diameter causes some HOMs leaking into the inner cladding and gradually vanish. Besides, the interference modes could also lead to the decrease of HOMs power in the CCTC fiber. According to the simulation results, Fiber IV has a better HOMs suppression along the fiber position, which is due to the smaller HOMs gain caused by the relatively smaller effective overlapping doping area and to the stronger HOMs leakage caused by the relatively steeper core diameter change trend in the region where the core diameter gradually decreases [31]. In addition, the  $M^2$  factor evolutions are also calculated, as shown in Fig. 1(c)–(d). It was found that, compared with a conventional uniform fiber, the CCTC fiber can effectively maintain a good beam quality along the fiber length during the power scaling.



Fig. 1. Simulation results of four types of fibers: (a) the core dimeter distribution, (b) fundamental mode (FM) power and HOM power (solid line, FM power distribution in fiber; dotted line, HOM power distribution in fiber), (c) M<sup>2</sup> factor evolution of Fiber I , and (d) M<sup>2</sup> factor evolution of Fiber IV.

To fabricate the CCTC YDF, a Yb/Al/Ce co-doped fiber preform was first produced using a conventional MCVD combined with solution doping technology. The refractive index profiles of the fiber preform (plotted in Fig. 2(a)) were measured at different positions along the preform using P104 (PHOTON KINETICS). It was shown that the refractive index distributions of the two interfaces are almost consistent, and exhibit an excellent uniformity along the longitudinal position of the preform. The refractive index difference ( $\Delta$ n) between the core and cladding is 1.45 × 10-3, and the corresponding core NA is ~0.065.

During the next step, the preform was post-processed before the fiber drawing, and a schematic diagram of post-processed preparation is shown in Fig. 3. Both ends of the preform are fixed and stretched to form several cones in the longitudinal direction while being heated at certain points using a  $H_2$ -O<sub>2</sub> flame (as shown in Fig. 3(a)). The stretched preform was ground into an octagon shape with a uniform outer diameter (as shown in Fig. 3(b)). Finally, the ground preform was drawn into a fiber with a cladding diameter of 400 µm and coated with a low-index polymer coating. The CCTC Yb-doped fiber can be selected from the two adjacent conical regions along the obtained fiber (as shown in Fig. 3(c)). The tapered ratio and the lengths of the different parts can be controlled during the tapering process of the preform. For the first CCTC fiber reported herein, the core shape was adopted to follow a parabolic function according to the simulation results.



Fig. 2. (a) Refractive index profile at different positions along the length of the preform and (b) the core diameter distribution of the fabricated CCTC fiber.



Fig. 3. Schematic diagram of the post-processed preparation.

The core diameter distribution along the axial direction of the CCTC fiber from the preform is shown in Fig. 2(b). The CCTC fiber can be divided into three regions along the length of the fiber, including two gradually varying small-sized regions at both ends, and a large-sized region in the middle. Region II is large core region with a core/cladding diameter of 31/400  $\mu$ m and length of approximately 4.8 m. Regions I and III are asymmetric conical regions: The core diameter of region I gradually transitions from 24.1 to 31.0  $\mu$ m, and the core diameter of region II gradually transitions from 23.4 to 31.0  $\mu$ m. The total length of this fiber is ~25 m, and the lengths of regions I and III are both 10.1 m. The average absorption coefficient was measured as ~1.54 dB/m at 976 nm. The equivalent core diameter of the fiber can be defined as follows [31]:

$$D_{eff}^{CCTC} = \frac{\int_{z=0}^{L} D(z) dz}{L} ,$$
 (2)

where D(z) is the diameter of the CCTC fiber along the z-direction and L is the length of the fiber. Here, the calculated equivalent core diameter of the CCTC fiber is ~27.3 µm.

# III. Application in high-power fiber laser

#### 3.1. Experiment setup

To evaluate the laser performance of the fiber, a CW all-fiber oscillator was established based on CCTC Yb-doped fiber. As shown in Fig. 4, the fiber oscillator was constructed as a bidirectional pumping configuration. A series of high-brightness 976-nm wave-band laser diode (LD) modules (maximum power of ~900 W for each) were employed as pump sources, which were injected into the gain fiber through forward and backward  $(6+1)\times 1$  pump/signal combiners. The core/inner-cladding diameters of the input and output signal fibers are 25/400 and 25/250 µm, respectively. The core/cladding diameters of the pump ports are 220/242 µm, which are identical to the pigtail fibers of the LD modules. A pair of fiber Bragg gratings (FBGs) was utilized as the resonant cavity mirror. Both the high-reflector FBG (HR-FBG) and the output coupler FBG (OC-FBG) were inscribed in the 25/400 µm passive fiber. The reflectivity of the HR-FBG and OC-FBG was 99.8% and 10.5% at a central wavelength of ~1080 nm, respectively. The 3-dB bandwidths of the HR-FBG and OC-FBG are 3.07 nm and 0.97 nm, respectively. The gain fiber used in the fiber oscillator is a homemade CCTC Yb-doped fiber, which is coiled in a racetrack groove of a water-cooled plate with a bending diameter of 12–17 cm. A schematic diagram of the longitudinal structure of the CCTC fiber is shown in the inset of Fig. 1. To deliver the signal laser, an ~3-m passive fiber with a core/inner-cladding diameter of 25/400 µm was spliced to the output port of the OC-FBG. The unabsorbed cladding light is removed by applying a cladding light stripper (CLS) to the passive fiber. A commercial quartz block head (QBH) with a pigtailed passive fiber was applied to avoid probable harmful feedbacks. All components of the fiber oscillator systems are cooled on the heat-sink plate to maintain efficient thermal management.

The laser performance of the CCTC Yb-doped fiber-based fiber oscillator, such as the output power, optical spectrum, beam quality, and time-domain signals of the laser were characterized during power scaling. The output spectra were monitored using an optical spectrum analyzer (OSA), and the temporal signals were measured using an InGaAs photodetector (PD), which is located at the center of the collimated light. The beam quality and beam profile of the output laser were measured using a beam quality analyzer (BQA).



Fig. 4. Experimental setup of an all-fiber laser oscillator system. (CO, collimator; HR, high reflector; PM, power meter; OSA, optical spectrum analyzer (Yokogawa, 600–1700 nm), PD, photodetector (Thorlabs, 150

MHz, 700-1800 nm), DM, dichroic mirror; BQA, beam quality analyzer (Beam Squared, Ophir)).

#### 3.2. Results and discussion

In the experiment, the backward and forward pumps were loaded successively in the laser system, and the relevant experimental results are as shown below. The measured output power and the corresponding optical-to-optical efficiency versus the pump power are shown in Fig. 5(a). The output power exhibits a linear increase with the injected pump power, and the maximum output power reaches 3.42 kW with an optical-to-optical efficiency of ~55.2%. The optical-to optical efficiency of this fiber oscillator is relatively lower than that of traditional uniform fiber oscillators [3, 4]. The relatively lower optical-to-optical efficiency can be mainly attributed to the following two aspects. One is the mode field mismatch between the YDF and the pump combiner. The YDF has a core diameter of  $\sim 24 \ \mu m$  at both ends, whereas the output signal fiber of the combiner is 25 µm, which causes a part of the signal light to leak into the cladding and is stripped by the CLS, especially in the fiber oscillator structure. In addition, the core region varying from a large core size to a small core size also inevitably reduce the optical efficiency, because a certain proportion of HOMs experience a higher bending loss owing to fiber coiling and thus leaks into the cladding. The output spectra of the fiber oscillator were measured at five different powers and are plotted in Fig. 5(b). Sufficient pump absorption and the employment of a cladding light stripper ensure that a clear signal is exhibited at ~1080 nm without a residual pump light. The spectral bandwidth of the signal laser broadens to ~5.58 nm at the maximum output power, which is mainly attributed to the nonlinear effects (such as selfphase modulation) in optical fibers. In addition, there is no obvious sign of Raman Stokes light observed at the maximum output power, indicating that this fiber oscillator has an excellent SRS suppression capability.



Fig. 5. (a) Output power and corresponding optical-to-optical efficiency of the laser. The blue and green regions represent the backward and forward pump scheme, respectively. (b) Output spectrum measured at different output powers, showing an SRS suppression ratio of >35 dB at the maximum power.

Temporal features of a laser are often used to evaluate the laser stability and occurrence of the TMI effect [32]. The measured PD signals and their corresponding Fourier transform spectra are plotted in Fig. 6. When the output power increases from 3022 to 3128 W, power fluctuations and frequency peaks are clearly presented on the time traces and their corresponding Fourier transform spectra, respectively. This means that the TMI effect occurs in the laser system. Furthermore, when the output power is further scaled to 3.42 kW, the temporal fluctuation becomes more violent and the Fourier transform frequency components broaden remarkably in the Fourier spectra, indicating that the laser operates from a transition state into a chaotic state. The calculated standard deviation (STD) of the temporal signal (plotted in Fig. 6(c)) also indicates the onset of the TMI, and the TMI threshold of the laser is  $\sim 3.12$  kW.





Fig. 6. (a) The normalized temporal signal at different output powers, (b) its corresponding Fourier transform spectra, and (c) the STD of the temporal signals at different output powers.

The beam quality (M<sup>2</sup> factor) of the output laser is also measured and is shown in Fig. 7(a) as a function of the output power. The measured  $M^2$  factor is approximately 1.6–1.7 in both the x-axis and y-axis before the occurrence of the TMI effect. The relatively poor beam quality can be mainly attributed to two reasons. First, the minimum V value at the output end of this CCTC fiber was calculated to be ~4.54, which could support several modes (LP<sub>01</sub>, LP<sub>11</sub>, LP<sub>21</sub>) and  $LP_{02}$ ) propagating in the fiber. Although fiber coiling was adopted as a mode filtering technique in the experiment, the bending loss was not enough to remove all the HOMs and obtain near single-mode beam quality. In addition, imperfect matching between the CCTC fiber and the output signal fiber of the combiners inevitably induces the excitation of the HOMs, which will deteriorate the beam quality. With the output power increasing to 3.42 kW, the M<sup>2</sup> factor deteriorates to 1.88, which is a direct sign of the onset of the TMI effect [9]. At an output power of 3022 W, the measured M<sup>2</sup> factor and the beam profile at the waist are as shown in Fig. 7(b). It can be seen from the inset of Fig. 7(b) that the beam spot was well maintained and there was no obvious mode distortion at this power level. Compared with the active tapered all-fiber laser oscillator in [29], which shares a close equivalent core diameter of ~25 µm, the fiber oscillator based on the CCTC fiber (equivalent core diameter of 27.3 µm) fiber has a higher output power and TMI threshold under our experimental conditions.



Fig. 7. (a) Measured beam quality evolution during the power scaling and (b)  $M^2$  factor and beam profile at 3022 W.

From the above experimental results, the CCTC Yb-doped fiber has shown a significant potential to achieve a high-power fiber laser oscillator with a near-diffraction-limited beam quality, although the TMI effect was observed at an output power of ~3.12 kW. It is important to note that the CCTC fiber has a constant cladding diameter and varying core diameter. The constant cladding can make the uniformity and concentricity of the fiber coating are much easier to be controlled in the fabrication process. Comparing with a traditional tapered fiber (the core and cladding vary simultaneously along the fiber) [29, 30], the constant cladding diameter of the CCTC fiber means a varying core-to-cladding ratio, which has a smoother thermal load profile along the fiber. In addition, the large core section provides a large mode area to suppress the SRS effect. The specially designed small core section can be designed to support a single-mode operation and thus enhance the TMI threshold. By further optimizing the CCTC fiber structure, such as the core diameter distribution and transverse refractive index distribution, combined with the confined-doped technology and ultra-low NA technology, in the future it is expected to achieve a higher output power without any sign of SRS and TMI effects.

## **IV. Conclusion**

In this paper, a novel long-tapered Yb-doped fiber, which we call CCTC fiber, was proposed and successfully fabricated in the lab using the MCVD method. Unlike all previously reported tapered fibers, the CCTC fiber consists of a uniform cladding (diameter of ~400  $\mu$ m) and a tapered core (diameter of ~24  $\mu$ m at both ends and ~31  $\mu$ m in the middle). The laser performance of this fiber has also been investigated in an LD pumped all-fiber oscillator and over 3 kW of output power was achieved with an optical-to-optical efficiency of ~55.2%. The

output power was scaled to a maximum value of 3.42 kW, where the beam quality (M<sup>2</sup> factor) degrades from 1.60 to 1.88. A better beam quality and further power scaling are promising for optimizing the fiber parameters. Because CCTC fibers with complex core structures can be produced from the MCVD and fiber drawing towers, they have significant potential for suppressing the nonlinear effects (such as SRS and SBS) and TMI effects in both CW and pulsed fiber lasers.

# Acknowledgement

This work was partly supported by the National Natural Science Foundation of China under grant nos. 61735007 and 61705266. The authors wish to thank Kun Zhang, Xiaoyong Xu, Tao Song, Chuanchuan Zhang, Siliu Liu, Lingfa Zeng, Yinchao Wan, and Zhejian Hong for their assistance during the experiment.

## References

- [1] C. Jauregui, J. Limpert, and A. Tünnermann, "High-power fibre lasers", Nat. Photonics 7, 861 (2013).
- [2] F. Beier, C. Hupel, S. Kuhn, S. Hein, J. Nold, F. Proske, B. Sattler, A. Liem, C. Jauregui, J. Limpert, N. Haarlammert, T. Schreiber, R. Eberhardt, and A. Tünnermann, "Single mode 4.3 kW output power from a diode-pumped Yb-doped fiber amplifier", Opt. Express 25, 14892 (2017).
- [3] B. Yang, H. Zhang, C. Shi, X. Wang, P. Zhou, X. Xu, J. Chen, Z. Liu, and Q. Lu, "Mitigating transverse mode instability in all-fiber laser oscillator and scaling power up to 2.5 kW employing bidirectional-pump scheme", Opt. Express 24, 27828-35 (2016).
- [4] K. Shima, S. Ikoma, K. Uchiyama, Y. Takubo, M. Kashiwagi, and D. Tanaka, "5-kW single stage all-fiber Ybdoped single-mode fiber laser for materials processing", Proc. SPIE **10512**, 105120C (2018).
- [5] F. Möller, R. G. Krämer, C. Matzdorf, M. Strecker, M. Plötner, F. Stutzki, T. Walbaum, T. Schreiber, R. Eberhardt, S. Nolte, and A. Tünnermann, "Multi-kW performance analysis of Yb-doped monolithic single-mode amplifier and oscillator setup", Proc. SPIE 10897, 108970D (2019).
- [6] Y. Wang, R. Kitahara, W. Kiyoyama, Y. Shirakura, T. Kurihara, Y. Nakanish, T. Yamamoto, M. Nakayama, S. Ikoma, and K. Shima, "8-kW single-stage all-fiber Yb-doped fiber laser with a BPP of 0.50 mm-mrad", Proc. SPIE **11260**, 1126022 (2020).
- [7] J. W. Dawson, M. J. Messerly, R. J. Beach, M. Y. Shverdin, E. A. Stappaerts, A. K. Sridharan, P. H. Pax, J. E. Heebner, C. W. Siders, and C. P. Barty, "Analysis of the scalability of diffraction-limited fiber lasers and amplifiers to high average power", Opt. Express 16, 13240-66 (2008).
- [8] M. N. Zervas, "Transverse mode instability, thermal lensing and power scaling in Yb3+-doped high-power fiber amplifiers", Opt. Express 27, 19019 (2019).
- [9] T. Eidam, C. Wirth, C. Jauregui, F. Stutzki, F. Jansen, H. Otto, O. Schmidt, T. Schreiber, J. Limpert, and A. Tünnermann, "Experimental observations of the threshold-like onset of mode instabilities in high power fiber amplifiers", Opt. Express 19, 13218-24 (2011).
- [10] R. Tao, P. Ma, X. Wang, P. Zhou, and Z. Liu, "Mitigating of modal instabilities in linearly-polarized fiber

amplifiers by shifting pump wavelength", J. Opt. 17, 45504 (2015).

- [11] R. Tao, R. Su, P. Ma, X. Wang, and P. Zhou, "Suppressing mode instabilities by optimizing the fiber coiling methods", Laser Phys. Lett. 14, 25101 (2016).
- [12] R. Tao, P. Ma, X. Wang, P. Zhou, and Z. Liu, "Theoretical study of pump power distribution on modal instabilities in high power fiber amplifiers", Laser Phys. Lett. 14, 25002 (2017).
- [13] K. Hejaz, M. Shayganmanesh, R. Rezaei-Nasirabad, A. Roohforouz, S. Azizi, A. Abedinajafi, and V. Vatani, "Modal instability induced by stimulated Raman scattering in high-power Yb-doped fiber amplifiers", Opt. Lett. 42, 5274 (2017).
- [14] A. V. Smith and J. J. Smith, "Increasing mode instability thresholds of fiber amplifiers by gain saturation", Opt. Express 21, 15168-82 (2013).
- [15] C. Jauregui, H. Otto, F. Stutzki, F. Jansen, J. Limpert, and A. Tünnermann, "Passive mitigation strategies for mode instabilities in high-power fiber laser systems", Opt. Express 21, 19375-86 (2013).
- [16] L. Dong, H. A. McKay, L. Fu, M. Ohta, A. Marcinkevicius, S. Suzuki, and M. E. Fermann, "Ytterbium-doped all glass leakage channel fibers with highly fluorine-doped silica pump cladding", Opt. Express 17, 8962-69 (2009).
- [17] X. Ma, C. Zhu, I. Hu, A. Kaplan, and A. Galvanauskas, "Single-mode chirally-coupled-core fibers with larger than 50µm diameter cores", Opt. Express 22, 9206-19 (2014).
- [18] D. Jain, C. Baskiotis, and J. K. Sahu, "Mode area scaling with multi-trench rod-type fibers", Opt. Express 21, 1448-55 (2013).
- [19] F. Stutzki, F. Jansen, T. Eidam, A. Steinmetz, C. Jauregui, J. Limpert, and A. Tünnermann, "High average power large-pitch fiber amplifier with robust single-mode operation", Opt. Lett. 36, 689-91 (2011).
- [20] M. Kashiwagi, K. Saitoh, K. Takenaga, S. Tanigawa, S. Matsuo, and M. Fujimaki, "Effectively single-mode all-solid photonic bandgap fiber with large effective area and low bending loss for compact high-power all-fiber lasers", Opt. Express 20, 15061-70 (2012).
- [21] V. Filippov, Y. Chamorovskii, J. Kerttula, K. Golant, M. Pessa, and O. G. Okhotnikov, "Double clad tapered fiber for high power applications", Opt. Express 16, 1929-44 (2008).
- [22] C. Shi, H. Zhang, X. Wang, P. Zhou, and X. Xu, "KW-class high power fiber laser enabled by active long tapered fiber", High Power Laser Sci. 6, 11-16 (2018).
- [23] K. Bobkov, A. Andrianov, M. Koptev, S. Muravyev, A. Levchenko, V. Velmiskin, S. Aleshkina, S. Semjonov, D. Lipatov, A. Guryanov, A. Kim, and M. Likhachev, "Sub-MW peak power diffraction-limited chirped-pulse monolithic Yb-doped tapered fiber amplifier", Opt. Express 25, 26958 (2017).
- [24] A. Fedotov, T. Noronen, R. Gumenyuk, V. Ustimchik, Y. Chamorovskii, K. Golant, M. Odnoblyudov, J. Rissanen, T. Niemi, and V. Filippov, "Ultra-large core birefringent Yb-doped tapered double clad fiber for high power amplifiers", Opt. Express 26, 6581-92 (2018).
- [25] Y. Zhu, M. Leich, M. Lorenz, T. Eschrich, C. Aichele, J. Kobelke, H. Bartelt, and M. Jäger, "Yb-doped large mode area fiber for beam quality improvement using local adiabatic tapers with reduced dopant diffusion", Opt. Express 26, 17034 (2018).
- [26] V. Filippov, Y. Chamorovskii, J. Kerttula, A. Kholodkov, and O. G. Okhotnikov, "600 W power scalable single transverse mode tapered double-clad fiber laser", Opt. Express 17, 1203-14 (2009).
- [27] V. Filippov, J. Kerttula, Y. Chamorovskii, K. Golant, and O. G. Okhotnikov, "Highly efficient 750 W tapered double-clad ytterbium fiber laser", Opt. Express 18, 12499-512 (2010).
- [28] V. Roy, C. Paré, B. Labranche, P. Laperle, L. Desbiens, M. Boivin, and Y. Taillon, "Yb-doped large mode area tapered fiber with depressed cladding and dopant confinement", Proc. SPIE **10083**, 1008314 (2017).
- 29] B. Yang, H. Zhang, C. Shi, X. Wang, Z. Pan, Z. Wang, P. Zhou, and X. Xu, "High power monolithic tapered ytterbium-doped fiber laser oscillator", Opt. Express 27, 7585 (2019).

- [30] Y. Ye, X. Xi, C. Shi, B. Yang, X. Wang, H. Zhang, P. Zhou, and X. Xu, "Comparative study on transverse mode instability of fiber amplifiers based on long tapered fiber and conventional uniform fiber", Laser Phys. Lett. 16, 85109 (2019).
- [31] C. Shi, X. Wang, P. Zhou, X. Xu, and Q. Lu, "Theoretical study of mode evolution in active long tapered multimode fiber", Opt. Express 24, 19473 (2016).
- [32] H. Otto, F. Stutzki, F. Jansen, T. Eidam, C. Jauregui, J. Limpert, and A. Tünnermann, "Temporal dynamics of mode instabilities in high-power fiber lasers and amplifiers", Opt. Express 20, 15710-22 (2012).